

## 1,4 BUTANEDIOL (BDO) PRODUCT SPECIFICATION

Analytical Parameters	Method	Unit	Value
Appearance	ASTM E 2680-9***	-	CFSM**
Color	ASTM D 1209-5	Pt/Co	Max. 5
Water Content	ASTM E 1064-5	ppm	Max. 500
Solidification Point	ASTM D 1493-97	°C	Min. 19.6
BDO Purity	HY379-1*	wt%	Min. 99.5
* GC Area % method. Water subtracted from Purity			
** Clear & free from suspended matter			
*** Test passes when suspended & or sediment particles sizes are >1mm but less than 3 nos. particles with size less than 1mm are not considered.			

Updated on January 2022

### Contact Details:

Website: [www.sipchem.com](http://www.sipchem.com)

Email:

Sales & Marketing [marketing@sipchem.com](mailto:marketing@sipchem.com)

Compliance & Product Stewardship Department [compliance@sipchem.com](mailto:compliance@sipchem.com)

### Disclaimer:

Before using the product listed above, customers and other users should take care in determining the suitability of such product for the intended use. SIPCHEM do not accept any liability whatsoever arising from the use of this information or the use, application or processing of any product described herein.